

Qualification of M-type cathode up to 4 A/cm² for space applications

Justin Demory¹, Jean-Michel Roquais¹, Frédéric André¹, Christof Dietrich², Jérôme Puech³

¹Thales AVS MIS, 2 rue Marcel Dassault 78141 Vélizy-Villacoublay, France

²Thales Deutschland, Söflinger-Straße 100, 89074 Ulm

³CNES, 18 avenue Edouard Belin, 31401 Toulouse Cedex 9, France

ABSTRACT


To obtain ever more powerful space TWT in particular in Q-band, cathode technology and models are constantly improved. Based on Thales in-orbit heritage with the M-type cathode up to 2.6 A/cm², we develop in this presentation a new approach based on time-to-knee measurement to adjust the operating cathode temperature. This cathode temperature adjustment method guarantees that the cathode can safely operate at 4 A/cm² for a space mission with a lifetime exceeding 15 years.

Two temperature constraints have to be managed to insure lifetime and reliability:

- The hotter the cathode, the shorter its lifetime. The electron emission decays when the cathode ages and this effect is compensated by increasing the anode voltage [1]. As shown in the figure, cathode temperature needs to remain below the 15 years line.
- The cathode has to emit enough current. Thales heritage shows that a good safety margin is defined with at least a factor 2 between J₀ (saturation current density) and J_n (nominal current density) at the operating temperature T_k at the beginning of life. Operation close to J₀ results in reduced quality of the electron beam. The corresponding line J₀ (T_k) = 2 J_n = 8 A/cm² is shown on the same graph and cathode must therefore operate above this line.

The space between these two lines shows that a M-type cathode can successfully fulfil its mission even with a spread on the initial J₀ and the temperature. The typical operating temperature of 990°C enables a lifetime exceeding 18 years at 4 A/cm².

This work is supported by THD-SAT project of the French Space Agency (CNES) in the frame of the program “Économie Numérique”, part of the PIA (“Programme d’Investissement d’Avenir”).



References

- [1] D. Dieumegard, J. Tonnerre, D. Brion and A. Shroff, “Life test performance of thermionic cathodes”, Applied Surface Science, vol. 111, pp. 84-89, 1997, proceedings of the IVESC 1996.